



Haycarb USA, Inc.

(Wholly owned subsidiary of Haycarb PLC)

612 Spring Hill Drive, Suite 140, Spring, TX 77386, USA

Toll Free: (855) HAYCARB Tel: (281)292 8678 Fax: (281)292 3423 Email: sales@haycarbusa.com

Website: www.haycarbusa.com

RWAP 1243

(NSF 61)

SPECIFICATION		VALUE	TEST METHOD
Iodine Number	(mg/g)	Min: 1000	ASTM D4607
Apparent Density	(g/cc)	Min: 0.52	ASTM D2854
Moisture (as packed)	(% by wt)	Max: 5	ASTM D2867
Total Ash	(% by wt)	Max: 3	ASTM D2866
Extractable pH		9-11	ASTM D3838
Hardness		Min 98	ASTM D 3802

PARTICLE SIZE 12x40 ASTM MESH

ASTM D2862

> 12 mesh	(1.700 mm)	(% by wt)	Max: 5
12x40	(1.700mm x 0.425mm)	(% by wt)	Min: 90
> 40 mesh	(0.425 mm)	(% by wt)	Max: 5



Haycarb PLC is
ISO9001:2008 and
ISO14001:2004 certified



Haycarb Activated Carbon grades that are tested and Certified by NSF International against NSF/ANSI Standard 42 for material requirements only, are listed on:
www.nsf.org/certified/EWTU

Component
Do not use with water that is microbiologically unsafe or of unknown quality without adequate disinfection before or after the system

